



# Modeling Woven Polymer Matrix Composites With MAC/GMC

Brett A. Bednarczyk  
Ohio Aerospace Institute, Brook Park, Ohio

## The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to [help@sti.nasa.gov](mailto:help@sti.nasa.gov)
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:  
NASA Access Help Desk  
NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076



# Modeling Woven Polymer Matrix Composites With MAC/GMC

Brett A. Bednarczyk  
Ohio Aerospace Institute, Brook Park, Ohio

Prepared under Cooperative Agreement NCC3-650

National Aeronautics and  
Space Administration

Glenn Research Center

## Acknowledgments

The author thanks Dr. Steven M. Arnold for helpful consultation regarding this investigation and for serving as contract monitor. This work was funded by NASA Contract NCC3-650.

Available from

NASA Center for Aerospace Information  
7121 Standard Drive  
Hanover, MD 21076  
Price Code: A03

National Technical Information Service  
5285 Port Royal Road  
Springfield, VA 22100  
Price Code: A03

Available electronically at <http://gltrs.grc.nasa.gov/GLTRS>

# MODELING WOVEN POLYMER MATRIX COMPOSITES WITH MAC/GMC

Brett A. Bednarczyk  
Ohio Aerospace Institute  
NASA Glenn Research Center M.S. 49-7  
21000 Brookpark Rd.  
Cleveland, OH 44135

## Abstract

NASA's Micromechanics Analysis Code with Generalized Method of Cells (MAC/GMC) is used to predict the elastic properties of plain weave polymer matrix composites (PMCs). The traditional one step three-dimensional homogenization procedure that has been used in conjunction with MAC/GMC for modeling woven composites in the past is inaccurate due to the lack of shear coupling inherent to the model. However, by performing a two step homogenization procedure in which the woven composite repeating unit cell is homogenized independently in the through-thickness direction prior to homogenization in the plane of the weave, MAC/GMC can now accurately model woven PMCs. This two step procedure is outlined and implemented, and predictions are compared with results from the traditional one step approach and other models and experiments from the literature. Full coupling of this two step technique with MAC/GMC will result in a widely applicable, efficient, and accurate tool for the design and analysis of woven composite materials and structures.

## 1. Introduction

Composites with woven reinforcements are attractive due to their ease of manufacture compared to unidirectional composites and laminates. Reinforcement preforms can be woven (or braided) into complex shapes that will remain intact prior to infiltration with the matrix material. This can reduce costs associated with machining as near net-shaped components can be fabricated. Woven reinforcements are particularly effective in polymer matrix composites (PMCs) applications where cost is often a driving design factor.

The beneficial qualities of woven composites come at a cost in terms of analysis; their thermo-mechanical behavior is significantly more difficult to model due to the complex and inherently three-dimensional geometry associated with the woven reinforcement. Typically, woven composites have been modeled either by considering a simplified geometric representation and using homogenization techniques (usually iso-stress and iso-strain assumptions) or via analysis of the actual three-dimensional geometry using finite element analysis (FEA). For recent reviews of such efforts, the reader is referred to Bednarczyk and Pindera (1997) and Bednarczyk and Pindera (2000a). In general, the drawbacks of these approaches involve the accuracy of the predictions, geometric generality, computational efficiency, the ability to admit local (constituent scale) sub-models (i.e., viscoplasticity, damage, micro failure), or suitability to function in the framework of broader component level analysis techniques.

A modeling approach that overcomes many of the aforementioned drawbacks is the method of cells, developed by Aboudi (1991). The generalization of this model, the generalized method of cells (GMC) (Paley and Aboudi, 1992), and the three-dimensional triply periodic version of GMC (Aboudi, 1995) increased the breadth of applicability of the original method of

cells considerably. The composite scale accuracy of GMC for modeling the thermo-mechanical behavior of continuous and discontinuous composites is well established. GMC also admits arbitrary doubly and triply periodic geometries, making the method completely general with respect to geometry (provided a geometric repeating unit cell can be identified). In its original form, GMC was quite computationally efficient as compared to FEA, see for instance Wilt (1995); however, the efficiency of the method was significantly increased via a reformulation by Pindera and Bednarczyk (1999) and Bednarczyk and Pindera (2000a). Since GMC provides the local stress and strain fields in simulated composite materials, it is ideal for inclusion of local sub-models, and, as it represents a material rather than a structure (such as a plate) it is well-suited for implementation in higher scale analysis techniques such as FEA.

Due to its useful characteristics summarized above, GMC was selected as the foundation for NASA Glenn Research Center's Micromechanics Analysis Code with Generalized Method of Cells (MAC/GMC) software package (Arnold et al., 1999). This product is available to (and in use by) U.S. industry and universities for composite design and analysis (see <http://www.grc.nasa.gov/WWW/LPB/mac/>). MAC/GMC takes advantage of GMC's beneficial properties and provides many additional features such as: i) the ability to simulate arbitrary thermo-mechanical loading histories, ii) a library of geometric repeating unit cells, iii) user-definable subroutines, iv) damage and local failure modeling, v) a library of elastic and viscoplastic material constitutive models, and vi) a seamless interface with the ABAQUS FEA package. Thus, MAC/GMC is an ideal candidate for modeling woven composite materials.

Bednarczyk and Pindera (2000a,b) used a stand-alone version of GMC (not MAC/GMC) to model a woven carbon/copper (C/Cu) metal matrix composite (MMC). In these studies, the original method of cells was used to represent the unidirectional infiltrated fiber yarns and embedded within the triply periodic version of GMC, which enabled representation of the composite's three-dimensional repeating unit cell. Local sub-models were incorporated to account for matrix plasticity and fiber-matrix debonding, allowing reasonably good agreement with experimental mechanical test data. However, due to GMC's inherent lack of coupling between the normal and shear stress and strain fields, the method has been unable to accurately model PMCs. In C/Cu, the dominant nature of the effects of matrix plasticity and fiber-matrix debonding muted the inaccuracies associated with GMC's lack of shear coupling, permitting accurate predictions for C/Cu. PMCs, on the other hand, can typically be modeled as elastic, and fiber-matrix debonding is often restricted to the near-failure regime of the PMC's response. Hence, GMC's predictions for the elastic properties of PMCs have been poor. Without the ability to predict accurately the effective properties of PMCs (the most common form of woven composites) the usefulness of GMC in modeling woven composites can be characterized as limited.

A concept that immediately exhibited potential for overcoming GMC's inability to model accurately woven PMCs was recently reported by Tabiei and Jiang (1999). These authors presented an approach to model a plain weave PMC in which, prior to homogenizing in the plane of the woven reinforcement, homogenization (via use of iso-stress and iso-strain assumptions) was performed *through the thickness of the weave*. As will be shown, Tabiei and Jiang's (1999) two step homogenization concept can be used in conjunction with MAC/GMC to enable accurate prediction of woven PMC elastic properties. Further, in the context of a fully embedded approach to modeling general woven and braided composites like that presented by Bednarczyk and Pindera (2000a,b), employing a through thickness homogenization step (before

homogenization in the plane of the weave, but after homogenization of the fiber and matrix to obtain the infiltrated yarn behavior) is clearly warranted.

## 2. Model

The reader is referred to Paley and Aboudi (1992) and Aboudi (1995) for a presentation of doubly and triply periodic versions of GMC, and to Pindera and Bednarczyk (1999) and Bednarczyk and Pindera (2000a) for the corresponding reformulations. In the present study, NASA's MAC/GMC software package was employed. It is a testament to the wide applicability of this software that it could be so readily applied to a problem for which it had not been designed.

To examine the ability of MAC/GMC to predict the elastic properties of a woven PMC, comparison will be made with the results of Naik and Ganesh (1992) for plain weave 42% e-glass/epoxy and plain weave 41% graphite/epoxy, and the results of Dasgupta et al. (1996) for plain weave 35% e-glass/epoxy. To this end, consider the geometry of a plain weave reinforcement shown in Fig. 1 as viewed from above. The warp and fill yarns undulate in and out of the plane to form the pattern depicted. Also shown in Fig. 1 is the repeating unit cell for the weave, which remains the same even when the weave is infiltrated with a matrix material to form a plain weave composite.

Figure 2 shows a MAC/GMC repeating unit cell that represents the geometry of a plain weave composite. Clearly, a more refined geometric representation of the composite is possible, but for the present study, the unit cell shown in Fig. 2 is sufficient. The traditional procedure for modeling the plain weave composite with GMC would be to first determine the effective (homogenized) behavior of the infiltrated fiber yarns that occupy the three-dimensional subcells in Fig. 2, and then to homogenize these three-dimensional subcells in one step via the triply periodic version of GMC. If local effects such as matrix plasticity, damage, or local failure are included, this procedure is not simple because an embedded local model is needed to represent the infiltrated fiber yarns. Bednarczyk and Pindera (2000a) used the method of cells as such a local model so that the stresses and strains in the fiber and matrix phases were known during the simulated thermo-mechanical loading history on the woven MMC. However, in the present case of a woven PMC, a local model is needed only to determine the effective elastic properties of the infiltrated fiber yarns. Arnold et al. (1999) used MAC/GMC to first determine the yarn elastic properties before analyzing a plain weave repeating unit cell (similar to that shown in Fig. 2), also with MAC/GMC. Here, for comparison with the results presented by Naik and Ganesh




Fig. 1. Top view of the plain weave geometry and repeating unit cell.




Fig. 2. MAC/GMC repeating unit cell used to represent a plain weave composite.

(1992), use will be made of the effective infiltrated fiber yarn properties given by these authors. These properties, which were determined via use of a composite cylinder assemblage model, are given in Table 1, along with the properties of the pure epoxy matrix material.

**Table 1. Elastic properties provided by Naik and Ganesh (1992) for the infiltrated fiber yarns and the epoxy matrix.**

Material	$V_f$	$E_A$ (GPa)	$E_T$ (GPa)	$G_A$ (GPa)	$G_T$ (GPa)	$\nu_A$
epoxy	—	3.5	3.5	1.3	1.3	0.35
e-glass/epoxy	0.70	51.5	17.5	5.80	6.60	0.31
graphite/epoxy	0.80	311.00	6.30	4.40	2.10	0.25

Dasgupta et al. (1996) did not provide the properties of the infiltrated fiber yarns in the 35% plain weave e-glass/epoxy composite that they modeled. These authors employed the Mori-Tanaka method to determine the properties from the fiber and matrix constitutive properties. In order to compare MAC/GMC results with the results of Dasgupta et al. (1996), the fiber and matrix properties employed by these authors were homogenized using MAC/GMC to obtain the effective properties of the e-glass/epoxy infiltrated fiber yarns. A  $26 \times 26$  MAC/GMC repeating unit cell (IDP 13, see Arnold et al. (1999)) was used for this purpose, and the resulting infiltrated yarn properties, along with the fiber and matrix properties are given in Table 2.

**Table 2. Elastic properties provided by Dasgupta et al. (1996) for the e-glass fiber and the epoxy matrix and the properties of the infiltrated e-glass/epoxy fiber yarns determined via MAC/GMC.**

Material	$V_f$	$E_A$ (GPa)	$E_T$ (GPa)	$G_A$ (GPa)	$G_T$ (GPa)	$\nu_A$
epoxy	—	3.45	3.45	1.26	1.26	0.37
e-glass	—	72.4	72.4	29.67	29.67	0.22
e-glass/epoxy	0.65	48.3	14.5	5.06	5.09	0.264



The dimensions of the repeating unit cell (defined as  $a$ ,  $g$ , and  $H$  in Fig. 2) were determined by first selecting  $a$  and then selecting  $g$  in order to yield the correct overall fiber volume fraction of the composite (given the infiltrated fiber yarn fiber volume fraction). Then, for the 42% e-glass/epoxy and the 41% graphite/epoxy,  $H$  was selected to yield the same quarter-cell aspect ratio  $[(a + g)/H]$  as the geometry employed by Naik and Ganesh (1992). Dasgupta et al. (1996) did not provide the dimensions of their 35% plain weave e-glass/epoxy composite, thus, for comparison with their results,  $H$  was selected to yield the same quarter cell aspect ratio as that employed by Naik and Ganesh (1992) for their e-glass/epoxy composite. Table 3 provides the unit cell dimensions; units are arbitrary. Note that the height of each through-thickness layer was taken as  $1/4$  of the overall unit cell height,  $H$  (see Fig. 2). Accordingly, the angle of inclination of the fibers was taken as  $\arctan(\pm H/2g)$  in the appropriate subcells.

**Table 3. Repeating unit cell dimensions.**

<b>Material</b>	<b>a</b>	<b>g</b>	<b>H</b>
42% e-glass/epoxy	1.00	0.67	0.50
41% graphite/epoxy	1.00	0.95	0.78
35% e-glass/epoxy	1.00	0.857	0.554

Given the above information, the effective elastic properties of the repeating unit cell shown in Fig. 2 can readily be determined using MAC/GMC's transversely isotropic elastic material constitutive model to represent the subcells. This model admits an arbitrary plane of transverse isotropy, thus enabling appropriate representation of all subcell materials present in Fig. 2. For more details on this procedure, see Example N in Arnold et al. (1999). Effective elastic properties for the plain weave e-glass/epoxy and graphite/epoxy composites predicted via this one step homogenization process are presented and discussed in Section 3.

An alternative two step approach, as mentioned previously, has been suggested by the work of Tabiei and Jiang (1999) and can be easily employed within the context of the MAC/GMC framework. Assuming the effective behavior of the infiltrated fiber yarns is known, a two step homogenization process wherein homogenization is performed through the thickness of the woven reinforcement prior to homogenization in the plane of the weave can be conducted. Examining the exploded view of the plain weave composite repeating unit cell employed previously (Fig. 3), it is clear that six unique types of through-thickness subcell groups exist. These six groups are shown in Fig. 4. Group 1 consists of subcells containing fibers oriented at  $0^\circ$  and  $90^\circ$  to each other in the plane of the weave. Groups 2, 3, 4, and 6 consist of two subcells of inclined fibers sandwiched between two pure matrix subcells. Finally, Group 5 contains only pure matrix subcells.

These six subcell groups are now homogenized independently via MAC/GMC. That is, the effective elastic properties of each group shown in Fig. 4 are determined by analyzing the group as if it were a triply periodic repeating unit cell. Clearly, Group 5 will have effective elastic properties identical to those of the epoxy matrix. The homogenized material represented by Group 1 is orthotropic, while those represented by Groups 2, 3, 4, and 6 are monoclinic. The effective stiffness matrices for Groups 1 – 4 and 6 are given in the Appendix for the two e-glass/epoxy composites and the graphite/epoxy composite. Note that both stacking sequences of the  $0^\circ$  and  $90^\circ$  subcells in Fig. 3 result in identical effective properties.




Fig. 3. MAC/GMC repeating unit cell for a plain weave composite – exploded view.




Fig. 4. Unique through-thickness subcell groups in the MAC/GMC repeating unit cell for a plain weave composite.

The second step in determining the effective elastic properties of the plain weave composite involves homogenizing the properties determined for the subcell groups in the plane of the woven reinforcement. This step was also performed using MAC/GMC and the corresponding repeating unit cell is shown in Fig. 5 where the numbers refer to the group numbers identified in Fig. 4. Clearly, by employing the effective material properties determined in step one, as shown in Fig. 5, the unit cell shown in Fig. 2 has been represented in a post through-thickness homogenization condition. It should be noted that MAC/GMC does not contain a monoclinic elastic material constitutive model in its libraries. The availability of user definable subroutines, however, made possible the use of the effective stiffness matrices given in the Appendix as direct input for the subcells in lieu of the typical engineering constants. Results generated for the plain weave e-glass/epoxy and graphite/epoxy composites are presented and discussed in Section 3.




Fig. 5. MAC/GMC repeating unit cell for a plain weave composite after through-thickness homogenization.

### 3. Results and Discussion

Figures 6 – 11 provide the predicted in-plane elastic properties of the 42% e-glass/epoxy and 41% graphite/epoxy woven composites. The MAC/GMC results are labeled as “1 step” and “2 step” in these figures. “1 step” refers to predictions made via homogenization of the repeating unit cell shown in Fig. 2 without first homogenizing through the weave’s thickness. “2 step” refers to utilization of the procedure described in Section 2 whereby homogenization is first performed through the thickness of the weave prior to the in-plane homogenization. All other results presented in Figs. 6 – 11 were taken from Naik and Ganesh (1992). These authors presented the slice array model (SAM) and two versions of the element array model (EAM), one in which the in-plane homogenization occurs first in parallel and then in series (PS) and the other in which this homogenization occurs in the reversed order (SP). The EAM in-plane homogenization is performed via use of iso-stress (series) and iso-strain (parallel) assumptions in the two in-plane coordinate directions. The order in which these directional homogenization schemes are applied gives rise to the two distinct EAM models (PS or SP), which, as indicated in Figs. 6 – 11, yield different predictions. For details on the EAM and SAM models, the reader is referred to Naik and Ganesh (1992).

Naik and Ganesh (1992) also provided additional simple model results to which their more refined EAM and SAM results were compared. These simple models are the modified mosaic parallel model (MMPM), which is an extension of the mosaic model developed by Chou and Ishikawa (1989), the modified Kabelka model (MKM), which is an extension of the model developed by Kabelka (1984), and the original Kabelka (1984) model. In addition, an experimental in-plane elastic modulus was provided by Naik and Ganesh for the e-glass/epoxy composite.

Examining Figs. 6 and 7, it is clear that utilization of the two step homogenization procedure with MAC/GMC rather than the traditional one step procedure significantly affects the in-plane elastic modulus predictions. For the plain weave e-glass/epoxy composite, the predicted modulus has increased from 13.4 GPa to 18.1 GPa, a change of 35%. The increase is even more dramatic for the graphite/epoxy composite, from 8.53 GPa to 17.4 GPa, or 104%. This greater increase is clearly due to the greater degree of transverse isotropy exhibited by the graphite/epoxy yarns compared to the e-glass/epoxy yarns (see Table 1). As mentioned previously, the low predicted in-plane elastic modulus associated with the one step MAC/GMC procedure is due to the lack of coupling between normal and shear stresses and strains in GMC. A manifestation of this lack of shear coupling is that each normal stress component is constant in rows of subcells along the stress component’s direction. That is, in Fig. 2,  $\sigma_{22}$  is constant in rows of subcells along the  $x_2$ -direction while  $\sigma_{33}$  is constant in rows of subcells along the  $x_3$ -direction. Thus, if a single compliant subcell is present in series with many stiff subcells, that compliant




Fig. 6. Predicted/experimental in-plane elastic modulus for plain weave 42% e-glass/epoxy.




Fig. 7. Predicted in-plane elastic modulus for plain weave 41% graphite/epoxy.




Fig. 8. Predicted in-plane shear modulus for plain weave 42% e-glass/epoxy.




Fig. 9. Predicted in-plane shear modulus for plain weave 41% graphite/epoxy.




Fig. 10. Predicted in-plane Poisson ratio for plain weave 42% e-glass/epoxy.




Fig. 11. Predicted in-plane Poisson ratio for plain weave 41% graphite/epoxy.

subcell must carry the same (appropriate component of) stress as the stiffer subcells. This then causes the entire row to have an unrealistically low stiffness, like a chain with a highly compliant link, as no stress can be transferred via shear to adjacent rows of subcells. This lack of shear coupling has a significant impact on the ability of the one step MAC/GMC procedure to predict accurately the in-plane modulus of woven composites as all rows of subcells contain compliant matrix only subcells or transversely-oriented composite subcells (see Fig. 3). Since the repeating unit cell lacks any complete subcell rows with continuous fibers, the one step approach underpredicts the in-plane modulus of the woven composite.

By homogenizing through the weave's thickness, the properties of the subcell groups (Fig. 4) are linked or "smeared" together. Then, in step two (see Fig. 5), two rows of subcells exist in both in-plane directions that do not contain any highly compliant subcells. This allows the two step MAC/GMC procedure to predict significantly more realistic in-plane elastic moduli for woven composites. This is illustrated via comparison with the other results given in Figs. 6 and 7. The two step MAC/GMC prediction for the in-plane elastic modulus compares well with the refined EAM and SAM models for both composites, and compares well with experiment for the plain weave e-glass/epoxy composite. Particularly encouraging is the fact that the two step MAC/GMC elastic modulus prediction falls between the EAM-PS and EAM-SP predictions for both woven composites. It should be noted that the EAM models employed 2500 individual geometric elements while the present MAC/GMC predictions were performed with a total of 64 subcells.

Examining Figs. 8 – 11, it is clear that the two step MAC/GMC homogenization procedure gives rise to higher in-plane shear moduli and lower in-plane Poisson ratios compared to the one step procedure. It appears that the MAC/GMC shear modulus predictions are improved via use of the two step procedure as they are in better agreement with the EAM and SAM model predictions. The Poisson ratio predictions of the one step MAC/GMC procedure are actually in better agreement with the EAM and SAM models than the corresponding two step MAC/GMC predictions.

Table 4 presents a comparison between MAC/GMC and the results of Dasgupta et al. (1996) for the 35% plain weave e-glass/epoxy composite. These authors employed a three-dimensional finite element unit cell model to predict the properties of the woven e-glass/epoxy composite. Dasgupta et al. (1996) also provided the experimental results given in Table 4. Recall that since Dasgupta et al. (1996) did not provide the dimensions of the composite, the geometry of the MAC/GMC repeating unit cell is approximate.

It is clear from Table 4 that the predictions of MAC/GMC have again been significantly improved through the utilization of the two step approach compared to the one step approach. As before, the in-plane modulus rises significantly (by 49%) resulting in much better agreement with experiment. Further, as before, the in-plane Poisson ratio has decreased significantly, but we now see that this decrease provides significantly better agreement with experiment. Thus it

**Table 4. Comparison of elastic property predictions and experiment (Dasgupta et al., 1996) for 35% plain weave e-glass/epoxy.**

	<b>E (GPa)</b>	<b><math>\nu</math></b>
Experiment	18.8	0.14
MAC/GMC – 1 step	11.4	0.183
MAC/GMC – 2 step	17.0	0.144
Dasgupta et al. (1996)	19.7	0.14

appears that the EAM models' Poisson ratio predictions (Figs. 10 and 11), which agreed well with the MAC/GMC one step prediction, may not be as accurate as those made using the MAC/GMC two step approach.

In Table 4 it is also clear that the three-dimensional FEA predictions performed by Dasgupta et al. (1996) are in better agreement with experiment than the MAC/GMC two step predictions. This is to be expected as this FEA employed a significantly more accurate geometric representation than that employed in this study (see Fig. 2). Utilization of a more refined unit cell geometry might improve the MAC/GMC predictions further.

#### 4. Summary/Conclusion

A two step homogenization procedure has been outline that enables the accurate prediction of woven PMC elastic properties with MAC/GMC. Previously, woven PMCs could not be accurately modeled using the GMC approach due to the lack of shear coupling inherent to the model. For woven MMCs, this lack of shear coupling was not prohibitive as the effects of matrix inelasticity and fiber-matrix debonding tended to dominate the woven MMCs' response. Via utilization of an independent through-thickness homogenization step, as suggested by Tabiei and Jiang (1999), MAC/GMC can now accurately model the response of the more common woven PMCs.

The results presented herein indicate that the two step MAC/GMC homogenization procedure predictions compare favorably with results from several previous models for woven composites and experiment. Rather than representing a significant achievement in and of themselves, these results serve as a proof of concept for this new MAC/GMC procedure for modeling woven composites. The next step will involve fully coupling this two step procedure with the embedded approach used previously to model woven MMCs (Bednarczyk and Pindera, 2000a,b), and incorporating these capabilities into NASA's MAC/GMC software package. This will, in effect, result in a multi-scale model for arbitrary woven and braided composite materials and structures, owing to MAC/GMC's interface with FEA. This multi-scale approach can be visualized as shown in Fig. 12. Via continuous localization and homogenization, the stress and strain fields in the fiber and matrix constituents can be tracked throughout the woven composite and structure during time dependent thermo-mechanical loading on the global (structure) scale. This will then allow employment of arbitrary visco-elasto-plastic constitutive models, damage models, and local failure criteria on the scale of the individual constituents.

It should be noted that the plain weave composite model developed by Tabiei and Jiang (1999) that introduced the concept of an independent through-thickness homogenization step also was linked with FEA. However, these authors' model localized only to the level of the infiltrated fiber yarns. Thus the constituent level fields were not available and micro scale constitutive, damage, and failure models could not be incorporated. Further, the work of Tabiei and Jiang (1999) considered only one particular woven composite architecture. Since the periodic composite microstructure admitted by MAC/GMC is arbitrary, the procedure outline herein can be employed for any type of woven or braided composite.




Fig. 12. Illustration of a multi-scale approach to modeling woven composite materials and structures.

## References

- Aboudi, J. (1991) *Mechanics of Composite Materials A Unified Micromechanical Approach*. Elsevier Science Publishing Co.: New York.
- Aboudi, J. (1995) "Micromechanical Analysis of Thermo-Inelastic Multiphase Short-Fiber Composites" *Composites Engineering*. 5(7), pp. 839-850.
- Arnold, S.M., Bednarczyk, B.A., Wilt, T.E., and Trowbridge, D. (1999) "Micromechanics Analysis Code With Generalized Method of Cells (MAC/GMC) User Guide: Version 3.0" *NASA/TM-1999-109070*.
- Bednarczyk, B.A. and Pindera, M.-J. (1997) "Micromechanical Modeling of Woven Metal Matrix Composites" *NASA-CR-204153*.
- Bednarczyk, B.A. and Pindera, M.-J. (2000a) "Inelastic Response of a Woven Carbon/Copper Composite – Part II: Micromechanics Model" *Journal of Composite Materials*. 34(4), pp. 299-331.
- Bednarczyk B.A. and Pindera, M.-J. (2000b) "Inelastic Response of a Woven Carbon/Copper Composite – Part III: Model-Experiment Correlation" *Journal of Composite Materials*. 34(5), pp. 352-378.
- Chou, T.-W. and Ishikawa, T. (1989) "Analysis and Modeling of Two-Dimensional Fabric Composites" in *Textile Structural Composites*. T.-W. Chou. and F.K. Ko eds., Elsevier: New York, pp. 209-264.
- Dasgupta, A., Agarwal, R.K., and Bhandarkar, S.M. (1996) "Three-Dimensional Modeling of Woven-Fabric Composites for Effective Thermo-Mechanical and Thermal Properties" *Composites Science and Technology*. 56, pp. 209-223.
- Kabelka, J. (1984) "Prediction of the Thermal Properties of Fibre-Resin Composites" in *Developments in Reinforced Plastics - 3*. G. Pritchard (ed.), Elsevier: London, pp. 167-202.
- Naik, N.K. and Ganesh, V.K. (1992) "Prediction of On-Axes Elastic Properties of Plain Weave Fabric Composites" *Composites Science and Technology*. 45, pp. 135-152.
- Paley, M. and Aboudi, J. (1992) "Micromechanical Analysis of Composites by the Generalized Cells Model" *Mechanics of Materials*. 14, pp. 127-139.
- Pindera, M.-J. and Bednarczyk, B.A. (1999) "An Efficient Implementation of the Generalized Method of Cells for Unidirectional, Multi-Phased Composites with Complex Microstructures" *Composites B*. 30, pp. 87-105.
- Tabiei, A. and Jiang, Y. (1999) "Woven Fabric Composite Material Model with Material Nonlinearity for Nonlinear Finite Element Simulation" *International Journal of Solids and Structures*. 36, pp. 2757-2771.
- Wilt, T.E. (1995) "On the Finite Element Implementation of the Generalized Method of Cells Micromechanics Constitutive Model" *NASA-CR-195451*.



## Appendix

Effective stiffness matrices for the subcell groups shown in Fig. 4. Units are GPa.

Group	42% e-glass/epoxy	41% graphite/epoxy
1	$\begin{bmatrix} 21.0 & 8.34 & 8.34 & 0 & 0 & 0 \\ & 39.0 & 8.93 & 0 & 0 & 0 \\ & & 39.0 & 0 & 0 & 0 \\ & & & 5.80 & 0 & 0 \\ & \text{sym.} & & & 6.17 & 0 \\ & & & & & 6.17 \end{bmatrix}$	$\begin{bmatrix} 8.43 & 3.70 & 3.70 & 0 & 0 & 0 \\ & 160. & 3.20 & 0 & 0 & 0 \\ & & 160. & 0 & 0 & 0 \\ & & & 4.40 & 0 & 0 \\ & \text{sym.} & & & 2.84 & 0 \\ & & & & & 2.84 \end{bmatrix}$
2	$\begin{bmatrix} 8.89 & 4.91 & 4.04 & 0 & 0 & 0.0395 \\ & 22.3 & 4.96 & 0 & 0 & 1.77 \\ & & 12.9 & 0 & 0 & 0.0231 \\ & & & 3.59 & -0.0437 & 0 \\ & \text{sym.} & & & 2.16 & 0 \\ & & & & & 2.19 \end{bmatrix}$	$\begin{bmatrix} 7.18 & 4.88 & 3.45 & 0 & 0 & 0.288 \\ & 30.1 & 3.34 & 0 & 0 & 5.22 \\ & & 6.98 & 0 & 0 & -0.0988 \\ & & & 2.60 & 0.281 & 0 \\ & \text{sym.} & & & 1.69 & 0 \\ & & & & & 2.21 \end{bmatrix}$
3	$\begin{bmatrix} 8.89 & 4.91 & 4.04 & 0 & 0 & -0.0395 \\ & 22.3 & 4.96 & 0 & 0 & -1.77 \\ & & 12.9 & 0 & 0 & -0.0231 \\ & & & 3.59 & 0.0437 & 0 \\ & \text{sym.} & & & 2.16 & 0 \\ & & & & & 2.19 \end{bmatrix}$	$\begin{bmatrix} 7.18 & 4.88 & 3.45 & 0 & 0 & -0.288 \\ & 30.1 & 3.34 & 0 & 0 & -5.22 \\ & & 6.98 & 0 & 0 & 0.0988 \\ & & & 2.60 & -0.281 & 0 \\ & \text{sym.} & & & 1.69 & 0 \\ & & & & & 2.21 \end{bmatrix}$
4	$\begin{bmatrix} 8.89 & 4.04 & 4.91 & 0 & -0.0395 & 0 \\ & 12.9 & 4.96 & 0 & -0.0231 & 0 \\ & & 22.3 & 0 & -1.77 & 0 \\ & & & 3.59 & 0 & 0.0437 \\ & \text{sym.} & & & 2.19 & 0 \\ & & & & & 2.16 \end{bmatrix}$	$\begin{bmatrix} 7.18 & 3.45 & 4.88 & 0 & -0.288 & 0 \\ & 6.98 & 3.34 & 0 & 0.0988 & 0 \\ & & 30.1 & 0 & -5.22 & 0 \\ & & & 2.60 & 0 & -0.281 \\ & \text{sym.} & & & 2.21 & 0 \\ & & & & & 1.69 \end{bmatrix}$
6	$\begin{bmatrix} 8.89 & 4.04 & 4.91 & 0 & 0.0395 & 0 \\ & 12.9 & 4.96 & 0 & 0.0231 & 0 \\ & & 22.3 & 0 & 1.77 & 0 \\ & & & 3.59 & 0 & -0.0437 \\ & \text{sym.} & & & 2.19 & 0 \\ & & & & & 2.16 \end{bmatrix}$	$\begin{bmatrix} 7.18 & 3.45 & 4.88 & 0 & 0.288 & 0 \\ & 6.98 & 3.34 & 0 & -0.0988 & 0 \\ & & 30.1 & 0 & 5.22 & 0 \\ & & & 2.60 & 0 & 0.281 \\ & \text{sym.} & & & 2.21 & 0 \\ & & & & & 1.69 \end{bmatrix}$

Group	35% e-glass/epoxy
1	$\begin{bmatrix} 18.7 & 7.82 & 7.82 & 0 & 0 & 0 \\ & 35.4 & 7.19 & 0 & 0 & 0 \\ & & 35.4 & 0 & 0 & 0 \\ & & & 5.06 & 0 & 0 \\ & \text{sym.} & & & 5.08 & 0 \\ & & & & & 5.08 \end{bmatrix}$
2	$\begin{bmatrix} 8.64 & 4.61 & 4.26 & 0 & 0 & 0.0223 \\ & 21.8 & 4.53 & 0 & 0 & 1.82 \\ & & 11.5 & 0 & 0 & -0.104 \\ & & & 3.18 & -0.00186 & 0 \\ & \text{sym.} & & & 2.07 & 0 \\ & & & & & 2.13 \end{bmatrix}$
3	$\begin{bmatrix} 8.64 & 4.61 & 4.26 & 0 & 0 & -0.0223 \\ & 21.8 & 4.53 & 0 & 0 & -1.82 \\ & & 11.5 & 0 & 0 & 0.104 \\ & & & 3.18 & 0.00186 & 0 \\ & \text{sym.} & & & 2.07 & 0 \\ & & & & & 2.13 \end{bmatrix}$
4	$\begin{bmatrix} 8.64 & 4.26 & 4.61 & 0 & -0.0223 & 0 \\ & 11.5 & 4.53 & 0 & 0.104 & 0 \\ & & 21.8 & 0 & -1.82 & 0 \\ & & & 3.18 & 0 & 0.00186 \\ & \text{sym.} & & & 2.13 & 0 \\ & & & & & 2.07 \end{bmatrix}$
6	$\begin{bmatrix} 8.64 & 4.26 & 4.61 & 0 & 0.0223 & 0 \\ & 11.5 & 4.53 & 0 & -0.104 & 0 \\ & & 21.8 & 0 & 1.82 & 0 \\ & & & 3.18 & 0 & -0.00186 \\ & \text{sym.} & & & 2.13 & 0 \\ & & & & & 2.07 \end{bmatrix}$



REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE August 2000	3. REPORT TYPE AND DATES COVERED Final Contractor Report		
4. TITLE AND SUBTITLE  Modeling Woven Polymer Matrix Composites With MAC/GMC		5. FUNDING NUMBERS  WU-242-23-52-00 NCC3-650		
6. AUTHOR(S)  Brett A. Bednarczyk				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  Ohio Aerospace Institute 22800 Cedar Point Road Brook Park, Ohio 44142		8. PERFORMING ORGANIZATION REPORT NUMBER  E-12422		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  National Aeronautics and Space Administration Washington, DC 20546-0001		10. SPONSORING/MONITORING AGENCY REPORT NUMBER  NASA CR-2000-210370		
11. SUPPLEMENTARY NOTES  Project Manager, S.M. Arnold, Structures and Acoustics Division, NASA Glenn Research Center, organization code 5920, (216) 433-3334.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Unclassified - Unlimited Subject Category: 24  This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  NASA's Micromechanics Analysis Code with Generalized Method of Cells (MAC/GMC) is used to predict the elastic properties of plain weave polymer matrix composites (PMCs). The traditional one step three-dimensional homogenization procedure that has been used in conjunction with MAC/GMC for modeling woven composites in the past is inaccurate due to the lack of shear coupling inherent to the model. However, by performing a two step homogenization procedure in which the woven composite repeating unit cell is homogenized independently in the through-thickness direction prior to homogenization in the plane of the weave, MAC/GMC can now accurately model woven PMCs. This two step procedure is outlined and implemented, and predictions are compared with results from the traditional one step approach and other models and experiments from the literature. Full coupling of this two step technique with MAC/GMC will result in a widely applicable, efficient, and accurate tool for the design and analysis of woven composite materials and structures.				
14. SUBJECT TERMS  Polymer matrix composites; Deformation; Woven architectures			15. NUMBER OF PAGES 20	
			16. PRICE CODE A03	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	